

STEEL TRADING CORPORATION OF AMERICA

"Oil Country Tubular Goods and Services"

GRADES	YIELD STRENGTH		TENSILE STRENGTH		HARDNESS
	MINPSI	MAXPSI	MINPSI	MAXPSI	MAXHRC
J-55	55000	80000	75000		---
K-55	55000	80000	95000		---
N-80	80000	110000	100000		---
L-80	80000	95000	95000		23
C-90	90000	105000	100000		25.4
C-95	95000	110000	105000		---
T-95	95000	110000	105000		25.4
P-110	110000	140000	125000		---
Q-125	125000	150000	135000		---



5800 Fifth St
Katy, TX 77493

Phone: 281.578.5383

Fax: 281.578.2568

Sales@SteelTradingCorp.com

www.SteelTradingCorp.com