


STEEL TRADING CORPORATION OF AMERICA

"Oil Country Tubular Goods and Services"

GRADES	YIELD STRENGTH		TENSILE STRENGTH		HARDNESS
	MINPSI	MAXPSI	MINPSI	MAXHRC	
J-55	55000	80000	75000	---	
K-55	55000	80000	95000	---	
N-80	80000	110000	100000	---	
L-80	80000	95000	95000	23	
C-90	90000	105000	100000	25.4	
C-95	95000	110000	105000	---	
T-95	95000	110000	105000	25.4	
P-110	110000	140000	125000	---	
Q-125	125000	150000	135000	---	



5800 Fifth St
Katy, TX 77493

Phone: 281.578.8805

Fax: 281.578.2568

Sales@SteelTradingCorp.com

www.SteelTradingCorp.com